



Deutsch: **Technisches Datenblatt** TPE/ SEBS 20° A

<b>0611</b>	<b>TPE/ SEBS 20° A, Stärke: 1 - 5 mm</b>	<b>Datum: 03.2014</b>
<b>Härte (ISO 868):</b>	20° ± 5° Shore A	
<b>Farbe:</b>	schwarz	
<b>Basismaterial:</b>	TPS – SEBS	
<b>Temperaturbereich:</b>	- 40° C bis + 100° C	
<b>Recycling:</b>	100 %	
<b>Spezifisches Gewicht (DIN EN ISO 1183-1 (A)):</b>	1,18 g/ cm <sup>3</sup>	
<b>Zugfestigkeit (DIN 53504 (S2 – cross)):</b>	2,8 MPa	
<b>Reißdehnung (DIN 53504 (S2 – cross)):</b>	830 %	
<b>Druckverformungsrest (DIN EN ISO 815):</b>	23° C / 72h / 11 % 70° C / 24h / 29 % 100° C / 24h / 69 %	

Jederzeitige Änderungen vorbehalten. Es obliegt dem Besteller, vor Verwendung des Produktes selbst zu prüfen, ob es sich auf mögliche anwendungswirksame Einflüsse für den von ihm vorgesehenen Verwendungszweck eignet. Alle in diesem technischen Datenblatt enthaltenen Angaben stellen Richtwerte dar.

RESOGOO® GmbH & Co KG  
Rolandskoppel 17, D-24784 Westerrönfeld  
Tel: +49-4331-43818-0  
Fax: +49-4331-43818-28

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)



English: **Technical data sheet**

**TPE/ SEBS 20° A**

---

<b>0611</b>	<b>TPE/ SEBS 20° A, thickness: 1 – 5 mm</b>	<b>date: 03.2014</b>
<b>hardness (ISO 868):</b>	20° ± 5° Shore A	
<b>colour:</b>	black	
<b>basic material:</b>	TPS – SEBS	
<b>temperature range:</b>	- 40° C bis + 100° C	
<b>recycling:</b>	100 %	
<b>specific gravity (DIN EN ISO 1183-1 (A)):</b>	1,18 g/ cm <sup>3</sup>	
<b>tensile strength (DIN 53504 (S2 – cross)):</b>	2,8 MPa	
<b>elongation at break (DIN 53504 (S2 – cross)):</b>	830 %	
<b>compression Set (DIN EN ISO 815):</b>	23° C / 72h / 11 % 70° C / 24h / 29 % 100° C / 24h / 69 %	

We reserve the right to make changes at any time. Before using the product, it is the responsibility of the purchaser to check for himself whether it is suitable for his intended use with regard to possible influences affecting the application. All data contained in this technical data sheet are approximate values.

---

**RESOGOO® GmbH & Co KG**  
Rolandskoppel 17, D-24784 Westerrönfeld  
**Tel: +49-4331-43818-0**  
**Fax: +49-4331-43818-28**

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)